



GEO TEXTILE 235 GSM



Features

Rot-proof

Resistant to mould, mildew, bacteria and rodents

Easy to lay

Extremely versatile

Resistant to UV rays

Indian Green Building Council
M E M B E R

ARDEX ENDURA (INDIA) PRIVATE LIMITED

Corporate Office & Regd. Office:
Unit No. 406 & 407, "Brigade Rubix",
No. 20, Yeshwanthapur Hobli, HMT Campus,
Bangalore - 560022, Karnataka, INDIA.
CIN No: U24233KA1997PTC022383
Tel: +91 80 66746500
Fax: +91 80 66746540
Email: customercare@ardexendura.com
Visit us: www.ardexendura.com

GEO TEXTILE 235 GSM



DESCRIPTION

Spunbond polyester nonwoven, needled one side and thermofixed.

		Average Value	Minimum
Weight	g/m ²	235	225
Thickness	mm	2.30	-
Tensile Strength at Break	daN / 5cm	MD	75
		CD	69
Elongation at Break	%	MD	55
		CD	65

NORM	SIZE	TEST PROCEDURE
ISO 9073 - 1	100 x 200 mm	Pressure : 2kPa Speed : 100 - 400mm/min 15 min at : 200°C
ISO 9073 - 2	2 500 mm ²	
ISO 9073 - 3	50 x 200 mm	
-	100 x 500 mm	

PRECAUTIONS

Keep out of reach of children, Wear suitable protective clothing, gloves and eyes/face protection. After contact with skin, wash immediately with plenty of clean water. In case of contact with eyes rinse immediately with plenty of clean water and seek medical advice.

For further information please refer to the Product Safety Data Sheet.

CONDITIONS OF SALE

Sold subject to the Company's conditions of sale which are available on request.

NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.