

WPT 300

Range of waterproofing tapes

DESCRIPTION

WPT 300 series is a range of waterproofing tapes which are made of non degradable material with outstanding flexibility and tear resistance. These tapes are specially designed for treating corners and construction joints while executing tiling and waterproofing works.

FEATURES

- High resistant to tear
- High durability & flexibility
- High stability during application
- Resistant to salts & chlorinates
- Easy to install

USES

- Construction joint treatment
- Treatment of dynamic cracks
- At corners and turnings
- Treatment of pipe penetrations, cut-outs
- Drywall waterproofing

TECHNICAL DATA & CHARACTERSTICS

	WPT 312	WPT 324
Colour	Light grey	Dark Grey
Material composition	Polyester non-woven, permanent anti-wicking finishing	Polyester non-woven, permanent anti-wicking finishing
Substrate	Thermoplastic elastomer, resistant to ageing, modified for better bonding	Thermoplastic elastomer, resistant to ageing
Coating		
Areas of Use	Drywall waterproofing and treatment of construction joints	Treatment of corners and cut-outs in water retaining structures & swimming pools
Total width/Coating width (Additional widths upon request)	120mm/70mm	240mm/140mm+100mm
Total thickness	approx. 0.60 mm	approx. 1.34 mm
Material weight	approx. 27 g/m	approx. 153 g/m
Resistance to Temperature	-30°C to +90°C	-30°C to +90°C
Roll length (Alternative make ups upon request)	50m	30m
Burst pressure: max.	3.0 bar	5 bar
Breaking load longitudinal DIN EN ISO 527-3	103 N / 15 mm	161 N / 15 mm
Breaking load lateral DIN EN ISO 527-3	39 N / 15 mm	56 N / 15 mm
Extension break longitudinal DIN EN ISO 527-3	28%	30%
Extension break lateral DIN EN ISO 527-3	146 %	139 %
Power absorption at 25% elasticity lateral DIN EN ISO 527-3	0.78 N /mm	2.39 N /mm
Power absorption at 50% Elasticity lateral DIN EN ISO 527-3	1.03 N / mm	3.03 N / mm
Resistance to water pressure DIN EN 1928 (Version B)	> 1.5 bar	> 3 bar
UV-Resistance: min.	500 h (DIN EN ISO 4892-2)	500 h (DIN EN ISO 4892-2)

WPT 300

Range of waterproofing tapes

CHEMICAL PROPERTIES

Resistance after storage over 7 days at room temperature in following chemicals

	WPT 312	WPT 324
Hydrochloric acid 3%	+	+
Sulphuric acid 35%	+	+
Citric acid 100g/l	+	+
Lactic acid 5% Internal	+	+
Potassium hydroxide 3%	+	+
Potassium hydroxide 20%	0	0
Sodium hypochlorite 0.3g/l	+	+
Salt water (20g/l Sea water salt)	+	+

Note: + resistant, 0 weakened, - non resistant

STORAGE

Store in cool and dry place, protect against sunlight, use within 24 months after receipt.

DISPOSAL

Disposal of empty packaging should be in accordance with local waste disposal authority regulations.

For further information please refer to the Material Safety Data Sheet.

CONDITIONS OF SALE

Sold subject to the Company's conditions of sale which are available on request.

NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

ARDEX ENDURA (INDIA) PRIVATE LIMITED

an ISO 9001:2008 certified company
Corporate Office & Regd. Office: Unit No. 406 & 407,
"Brigade Rubix" No. 20, HMT Campus,
Yeshwantpur Hobli, Bengaluru - 560013.
CIN No: U24233KA1997PTC022383 Tel: +91 80 66746500
Email: customercare@ardexendura.com
Website: www.ardexendura.com

Branches

• AHMEDABAD	079 26425310	• HUBBALLI	0836 2970505	• PATNA	+919934687909
• AURANGABAD	+918888480847	• HYDERABAD	040 27650293	• PUNE	020 64781879
• BENGALURU	080 40912934	• INDORE	0731 4021148	• RAIPUR	0771 6539055
• BHUBANESHWAR	0674 2421901	• JAIPUR	0141 2392993	• SALEM	0427 2211454
• CALICUT	0495 2740334	• KOLKATA	033 65090604	• SHIVAMOGGA	+919880605770
• CHENNAI	044 42805544	• LUCKNOW	0522 4043251	• TRICHY	0431 6454649
• DELHI	011 26802949	• LUDHIANA	0161 2532170	• TRIVANDRUM	0471 2598648
• ERNAKULAM	0484 2341044	• MANGALURU	0824 2442176	• VIJAYAWADA	+918688354587
• GHAZIABAD	0120 6541564	• MUMBAI	022 65133299	• VISAKAPATNAM	0891 6469499
• GOA	0832 2750992	• MYSURU	0821 2570171		
• GUWAHATI	+917896002188	• NAGPUR	+919822223743		

