



B 35

Structural grade, polymer modified cementitious repair mortar

DESCRIPTION

B 35 is a two component mortar consisting of a blend of cement, graded fillers and chemical additives along with a liquid polymer to provide a mortar that ensures high strength and long-term durability. It is recommended for vertical and horizontal structural repairs.

USES

- All types of structural repair that can be applied by trowel
- Repair of beams, columns, walls and slabs in high rise buildings
- Repair of Marine structures
- Industrial floors patch repair
- Repair of structural members subjected to loading

FEATURES

- High strength: suitable for structural repair
- Good bond to cementitious substrate
- Slump free: ideal for vertical (upto 40mm) and horizontal (upto 100mm) repairs
- Shrink free: reduces the risk of cracks

PHYSICAL PROPERTIES

B 35 @ 27 ± 1°C

Bulk density of powder	1.48 - 1.52 g/cc
Mix density	2.10 - 2.20 g/cc
Initial set approx.	3 hours
Final set approx.	5 hours
Working time	30 minutes

Compressive Strength

After 1 day	>14 N/mm ²
After 28 days	>49 N/mm ²

Flexural Strength

After 28 days	7 N/mm ²
---------------	---------------------

Temperature resistance 0°C - 60°C

VOC Content 161 g/l

COVERAGE ESTIMATES

Pack size	Coverage
20.20 kg	Approximately 1 m ²
PART A 20kg	@ 10 mm thickness
PART B 200ml	

APPLICATION INSTRUCTIONS

Identification of repair area and substrate preparation

The edges of the repair area should be cut vertically to a minimum of 10 mm to ensure no feather edging. The substrate must be hard, sound and free of dust, dirt and other loose material. Pre-wet the substrate thoroughly with clean water. Situations where pre-wetting is difficult, one coat of E 135 should

be brush applied as a bonding coat. B 35 should be applied when the bond coat is still tacky.

Mixing

Add 2.60 litres of potable water in a clean mixing container. Add Part B liquid and mix the material using heavy duty mixer or forced action mixer. Add Part A powder to the same container and mix thoroughly for 2 - 3 minutes to obtain a lump free and slump resistant mortar.

Placing of mortar

Apply the mixed mortar using a trowel or gloved hand to the prepared substrate to required thickness. Thoroughly compact the mortar on to the prepared substrate. The mixed mortar has a working time of 30 minutes. The material may be finished with trowel to provide a suitable finish. The mixed mortar sets after 5 hours.

Curing

B 35 should be cured with C 20 curing compound or clear polythene sheeting over wet hessian immediately after placing.

CLEANING

B 35 can be removed from tools and equipment by washing in clean water immediately after use. Any hardened material will need to be removed mechanically.

STORAGE AND SHELF LIFE

B 35 must be stored in unopened packaging, clear of the ground in cool dry conditions and be protected from excessive draught. If stored correctly, as detailed above, the shelf life of this product is 12 months from the date shown on the packaging.

PRECAUTIONS

Avoid contact with eyes and prolonged contact with the skin. Care should be taken to avoid inhalation or ingestion of dust and prevent contact with the eyes. In case of contact with eyes, flush with ample amount of clean water and seek medical advice if necessary.

DISPOSAL/SPILLAGE

Spillage of any of the component products should be absorbed onto sand or other inert materials and transferred to a suitable disposable vessel. Disposal of such spillage or empty packaging should be in accordance with local waste disposal authority regulations.

For further information please refer to the Material Safety Data Sheet.

CONDITIONS OF SALE

Sold subject to the Company's conditions of sale which are available on request.

B 35

Structural grade, polymer modified cementitious repair mortar

NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

ARDEX ENDURA (INDIA) PRIVATE LIMITED

an ISO 9001:2015 & ISO 14001:2015 certified company
Corporate Office & Regd. Office: Unit No. 406 & 407,
"Brigade Rubix" No. 20, HMT Campus,
Yeshwanthpur Hobli, Bengaluru - 560013.
CIN No: U24233KA1997PTC022383 Tel: +91 80 66746500
Email: customercare@ardexendura.com
Website: www.ardexendura.com

Branches

• AHMEDABAD	079 26425310	• HUBBALLI	0836 2970505	• NAGPUR	+919822223743
• AURANGABAD	+918605445577	• HYDERABAD	040 27650293	• PATNA	+919934687909
• BENGALURU:	080 40912934	• INDORE	0731 4021148	• PUNE	+919028811555
• BHUBANESHWAR	0674 2578101	• JAIPUR	0141 2441893	• RAIPUR	0771 4038300
• CALICUT	0495 2740334	• KOLKATA	+919831071084	• SALEM	0427 2271454
• CHENNAI	044 42805544	• LUCKNOW	0522 4043251	• SHIVAMOGGA	+919880605770
• DELHI	011 26384711	• LUDHIANA	0161 2532170	• TRICHY	+919894766109
• ERNAKULAM	0484 2341044	• MANGALURU	0824 2442176	• TRIVANDRUM	0471 2598648
• GOA	0832 2750992	• MUMBAI	022 65133299	• VIJAYAWADA	+918688354587
• GUWAHATI	+917896002188	• MYSURU	+919880000683	• VISAKAPATNAM	0891 6469499

