

R 33 CE

Epoxy coving mortar

DESCRIPTION

R 33 CE is a three component, high performance, trowel applied epoxy mortar designed for use as coving in areas where cleanliness and hygiene is of prime importance. It has outstanding wearing properties with high chemical resistance. Ideally suited for aggressive areas where a seamless, joint free finish is required.

USES

- Laboratories & clean rooms
- Food and beverage production
- Abattoirs
- Dairies
- Pharmaceutical manufacturing
- Warehouses and storage areas

FEATURES

- Tough & hard wearing: durable with low maintenance cost
- Good abrasion resistanc
- Resistant to a wide range of chemicals and liquids
- Seamless: easily cleanable to maintain high standards of hygiene
- Hygienic and non-tainting
- Supplied in pre-measured packs for ease of mixing and consistency at site

PHYSICAL PROPERTIES

R 33 CE	@ 27 ± 1°C
Mixed density	1.60 g/cc
Pot life	45 mins
Drying Times Setting time Full cure	48 hrs 7 days
Bond strength (7 days)	> 1.5 N/mm ²
Compressive strength	70 N/mm ²
Flexural strength	23 N/mm ²
Tensile strength	11 N/mm ²

COVERAGE ESTIMATES

Pack sizeCoverage16.50 kgApprox. 9.0 RMT @ 2"x2" thickPart A 1 kgApprox. 6.5 RMT @ 3"x3" thickPart B 500 gPart C 15 kg

APPLICATION INSTRUCTIONS

Surface Preparation

Note: The substrate should have a surface tensile strength of at least 1.5 $\mbox{N/mm}^2\,$.

The substrate must be hard, sound and free of dust and other barrier materials such as paint, lime coatings, plaster, curing agents, laitance, adhesive residues etc., which will inhibit adhesion to the substrate. All vertical surfaces must be of a rigid construction to resist deflection during the application process. Use a suitable degreaser to remove polish, wax, grease, oil and similar contaminating substances prior to mechanical preparation.

Contaminated substrates should be mechanically prepared, either by grinding or contained shot blasting equipment or similar, and be vacuumed clean. Overwatered or otherwise weak concrete surfaces must also be suitably prepared down to sound, solid concrete by mechanical methods. Dust and other debris should be removed using vacuum equipment.

Priming

All areas to be treated with R 3 E or R 9 CE must be first primed with a suitable epoxy primer from the ARDEX ENDURA range. Selection of the primer must be made depending on the substrate condition & porosity. Please refer to the individual primer data sheets for further details.

One or more coats of the primer may be required depending upon the condition and porosity of the concrete substrate. High porosity substrates may be revealed after preparation and will be evident by their rapid suction and absorption. Poorly primed surfaces may lead to blistering or pin holing in the cured resin.

Mixing

The individual contents Part A & Part B should be thoroughly stirred before being mixed together. The entire contents of Part A and Part B should be poured in to a larger mixing vessel to incorporate the Part C. Mix thoroughly with a spiral mixing paddle in a slow speed drill. Finally the Part C is added to the same container and continue mixing for two minutes to obtain a consistent homogenous mix. One or more packs may be mixed at the same time in order to maintain a quick rate of installation.

Application

The mixed material should be applied onto the prepared and primed tacky surface without delay using a trowel to achieve the desired thickness and coving profile.

Note:

- Do not overwork the surface and do not mix more than can be used within the working time. The work area should be protected during the installation process and during the initial curing time to ensure that no airborne debris can contaminate the surface of the wet resin as this will lead to unwanted blemishes in the hardened and cured surface.
- All movement joints in the substrate must be carried through the coving and properly sealed. Construction joints and cracks not subject to movement may be overlaid but should the substrate move in anyway, these defects will reflect through the coving.

R 33 CE

Epoxy coving mortar

LIMITATIONS

The product should not be applied in temperatures less than 10 C or where the ambient relative humidity (RH) is greater than 85%.

CLEANING

R 33 CE can be removed from tools and equipment by using RTC 100 immediately after use. Any hardened material will need to be removed mechanically.

STORAGE AND SHELF LIFE

R 33 CE has a shelf life of 12 months if kept in a dry, clean store between 5°C and 30°C in the original unopened containers. The product should be protected from frost, away from direct sunlight and sources of heat.

PRECAUTIONS

During mixing and application the following precautions should be observed: Ensure adequate ventilation and avoid contact of the material with the eyes, nasal passages, mouth and unprotected skin. Avoid contact with the hands by wearing protective gloves and by using, if necessary, a suitable barrier cream. In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice and after contact with the skin wash immediately with plenty of soap and water. Prolonged contact with the skin should be avoided, especially where the user has an allergic reaction to resin-based materials. Always wear gloves and eye/face protection as necessary. Observe personal hygiene, particularly washing the hands after work has been completed or at any interruption whilst work is in progress. Care should be taken when removing gloves to avoid contaminating the insides. In case of accidents seek medical advice.

DISPOSAL/SPILLAGE

Spillage of any of the product components should be absorbed onto sand or other inert materials and transferred to a suitable disposable vessel. Disposal of such spillage or empty packaging should be in accordance with local waste disposal authority regulations.

For further information please refer to the Material Safety Data Sheet.

CONDITIONS OF SALE

Sold subject to the Company's conditions of sale which are available on request.

NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

ARDEX ENDURA (INDIA) PRIVATE LIMITED

an ISO 9001:2015 & ISO 14001:2015 certified company Corporate Office & Regd. Office: Unit No. 406 & 407, "Brigade Rubix" No. 20, HMT Campus, Yeshwanthpur Hobli, Bengaluru - 560013. CIN No: U24233KA1997PTC022383 Tel: +91 80 66746500 Email: customercare@ardexendura.com Website: www.ardexendura.com

Br	anches
•	AHMEDABAD

AURANGABAD

BHUBANESHW

CALICUT

CHENNAI

DELHI

• GOA

ERNAKULAM

BENGALURU

+9198106 03431

0484 2341044

0832 2750992

	+9192	28019132	•	GUWAHATI	+917	896002188	•	MUMBAI
	+9186	05445577	•	HUBBALLI	0836	2970505	•	MYSURL
	+9199	72922333	•	HYDERABAD	+919	703250099	•	NAGPUR
/AR	0674	2578101	•	INDORE	0731	4021148	•	PUNE
	0495	2740334	•	JAIPUR	0141	2441893	•	RAIPUR
	044	42805544	•	KOLKATA	+919	831071084	•	SALEM

INDURE	0/31	4021148
JAIPUR	0141	2441893
KOLKATA	+9198	33107108
LUCKNOW	0522	4043251
LUDHIANA	0161	2532170
MANGALURU	0824	2442176

Indian Green Building Council	
MEMBER	

TRIVANDRUM

VIJAYAWADA

VISAKAPATNAM



022 65133299

0821 2570171 +919822223743

+919881249292

0771	4038300	
0427	2211454	
0471	2598648	
+918688354587		
0891	6469499	