



# WPM 004 Flex

## High Performance Acrylic Reinforced Waterproof Coating

### DESCRIPTION

WPM 004 Flex is a two component, cementitious waterproofing compound designed for use in areas where substrates are subjected to movement and crack bridging properties are desired. It has been formulated with advanced acrylic polymer technology to increase its flexibility and water resistance.

### STANDARDS

Conforms to the Global Migration Standards laid down in 21 CFR 175 - 300 (April 1, 2019) of US - FDA for intended use for contact with aqueous food products.

### USES

- Fibre Cement Board, Plasterboard, Plywood, Particle Board (marine grade)
- Swimming Pools (Suspended and Below Ground)
- Wet areas & commercial kitchens
- Terraces and Balconies
- Water tanks
- Retaining walls

### FEATURES

- Flexible: accommodates normal building movements and hairline cracks
- Resists both positive and negative pressure
- UV stable: Can be left exposed
- Easy to apply: By brush, roller or spray
- Water based: safe to use, low odour & easy cleaning
- Excellent bond to concrete, masonry, ceramics and most common substrates\*
- Self-primed: No additional primer required
- Nontoxic: Can be safely used as internal waterproofing of potable water tanks
- Allows water vapour to escape from the substrate.

\*Necessary mechanical surface preparation is required

### PHYSICAL PROPERTIES

WPM 004 Flex	@ 27 ± 1°C
Appearance	Grey colour, Homogeneous, with brushable consistency
Mixed material density	1.5 g/cc
Pot life	3 hours
Re-coat time	2 - 3 hours
Elongation @ 7 days (ASTM D 412)	>200%
Adhesion to Concrete (ASTM D 4541)	>1.20 N/mm <sup>2</sup>
Crack Bridging Capability upto 2mm (ASTM C836)	Pass
No Crack after 10 Cycle of stretching and closing at 1mm width (ASTM C836)	Pass
Water Vapour Transmission (ASTM E 96)	1.12g /m <sup>2</sup> /24hrs

Tensile Strength	>2.0 N/mm <sup>2</sup>
VOC Content	24 g/L

### COVERAGE ESTIMATES

Pack size	Coverage
42 kg	Approx. 24 m <sup>2</sup> / pack
Powder 23 kg	in two coats.
Liquid 19 kg	

### APPLICATION INSTRUCTIONS

#### Surface Preparation

The surface to be treated must be dry, clean, structurally sound, free from oil, grease, wax, polish, laitance, dust and other barrier materials. All vertical bore packing shall be treated using B 30 (non-shrink cementitious structural grout) and all horizontal bore packing shall be treated using polymer modified mortar admixed with E 135.

Covings, if required, shall be installed using polymer modified mortar admixed with E 135 (SBR, multipurpose concentrated liquid polymer additive and bonding agent). Alternatively, on non-sunken floors WPT 312 coving bandage can be used to avoid thick covings.

#### Mixing

The liquid should be thoroughly stirred and poured in a suitable mixing vessel. Slowly add the powder and mix with spiral mixing paddle in a slow speed drill. Continue until a consistent homogenous mix is achieved.

#### Application

Saturate the surface with clean water. Whilst wet, but free of standing water, apply two coats of 'WPM 004 Flex' using a short, stiff bristle brush or roller. Leave the first coat to dry for 2 - 3 hours before starting the second coat. The second coat should be applied at right angle to the first coat. Allow the membrane to dry completely before tiling or subsequent finishes.

Application Thickness Per Coat	Approx. 0.6mm
Coat Consumption (min 2 Coats)	Approx. 24 m <sup>2</sup>
Consumption of 2 Coats (kg/m <sup>2</sup> )	Approx. 1.7 kg (depending on substrate condition)

#### CLEANING

Wash hands, brushes, rollers, etc with water while the material is still fresh. Remove cured material mechanically.

#### STORAGE AND SHELF LIFE

WPM 004 Flex has a shelf life of 12 months if kept in a dry, clean store between 5°C and 30°C in the original unopened containers. The product should be protected from frost, away from direct sunlight and sources of heat.

# WPM 004 Flex

## High Performance Acrylic Reinforced Waterproof Coating

### PRECAUTIONS

During mixing and application, the following precautions should be observed: ensure adequate ventilation and avoid contact of the material with the eyes, nasal passages, mouth and unprotected skin. Avoid contact with the hands by wearing protective gloves. In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice. Observe personal hygiene, particularly washing the hands after work has been completed or at any interruption whilst work is in progress. In case of accidents seek medical advice.

### DISPOSAL/SPILLAGE

Spillage of any of the product components should be absorbed onto sand or other inert materials and transferred to a suitable disposable vessel. Disposal of such spillage or empty packaging should be in accordance with local waste disposal authority regulations.

### CONDITIONS OF SALE

Sold subject to the Company's conditions of sale which are available on request.

### NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.



### ARDEX ENDURA (INDIA) PRIVATE LIMITED

an ISO 9001:2015 & ISO 14001:2015 certified company  
Corporate Office & Regd. Office: Unit No. 406 & 407,  
"Brigade Rubix" No. 20, HMT Campus,  
Yeshwanthpur Hobli, Bengaluru - 560013.  
CIN No: U24233KA1997PTC022383 Tel: +91 80 66746500  
Email: [customercare@ardexendura.com](mailto:customercare@ardexendura.com)  
Website: [www.ardexendura.com](http://www.ardexendura.com)

#### Branches

• AHMEDABAD	+919228019132	• GUWAHATI	+917896002188	• MUMBAI	022 65133299
• AURANGABAD	+918605445577	• HUBBALLI	0836 2970505	• MYSURU	0821 2570171
• BENGALURU	+919972922333	• HYDERABAD	+919703250099	• NAGPUR	+919822223743
• BHUBANESHWAR	0674 2578101	• INDORE	0731 4021148	• PUNE	+919881249292
• CALICUT	0495 2740334	• JAIPUR	0141 2392993	• RAIPUR	0771 4038300
• CHENNAI	044 42805544	• KOLKATA	+919831071084	• SALEM	0427 2211454
• DELHI	+919811810923	• LUCKNOW	0522 4043251	• TRIVANDRUM	0471 2598648
• ERNAKULAM	0484 2341044	• LUDHIANA	0161 2532170	• VIJAYAWADA	+918688354587
• GOA	0832 2750992	• MANGALURU	0824 2442176	• VISAKAPATNAM	0891 6469499