



K 180

High Strength Self-leveling Compound

DESCRIPTION

K 180 is a rapid hardening self leveling compound, walkable after approximately 4 hours and ready for use after 24 - 72 hours. Grey powder with special cements, high quality synthetic resins, selected fillers and other special additives.

FEATURES

- High Strength Self – levelling Compound, heavy duty for industrial flooring
- Internal use
- Pumpable
- Rapid hardening – walkable after approx. 4 hours

AREAS OF APPLICATION

- Dry, internal, cementitious sub-floors.
- Filling, smoothing and leveling of concrete slabs and cementitious screeds prior to application of industrial flooring coatings such as epoxies and polyurethanes.
- Heavily trafficked industrial floors such as production workshops and warehouses.

SUBSTRATE PREPARATION

Principally, the substrate must be mature, sound, solid, clean and dry with good surface integrity – in other words, sufficiently cured, firm, load bearing and free from all contaminants such as dust, laitance, oil & grease, adhesive & coating residues, release agents, curing compounds, etc.

Use suitable degreaser to remove polish, wax, grease, oil and similar contaminating substances.

Concrete floors must be at least 4 weeks old. Mechanically prepare the substrate surface using recommended preparation methods such as shot-blasting, scarifying, diamond grinding, shaving or other suitable methods to provide a roughened, clean, sound, solid and open porous surface.

Acid etching is not an acceptable method of cleaning the subfloor. Do not use solvents or sweeping compounds.

Repair minor defects such as superficial cracking and holes using an appropriate ARDEX ENDURA product, ie: A 45 or solvent-free liquid epoxy. All joints and cracks subject to movement must be brought through to the final floor finish and suitably detailed for the particular application.

Substrates where the measured moisture level is above 5.5% or 70% by Relative Humidity (RH) test method must first be sealed with WPM 300 prior to any leveling installation.

Direct to earth sub-floors must be protected from rising damp by containing a functioning damp-proof membrane (DPM) – if this is not included underneath the substrate, then use WPM 300.

After suitable preparation, the substrate must be thoroughly vacuumed and properly primed for a successful installation.

For further information,

For further information, contact ARDEX ENDURA Technical Services.

PRIMING

P 51 (pre-diluted with water) should be applied to porous or rough absorbent substrates. Apply evenly with a bristle push broom. Allow to dry to a thin, clear film (minimum 1 hour - maximum 24 hours). Very absorbent substrates may require 2 coats of diluted P 51 primer. Allow each coat to dry sufficiently before proceeding.

On dense or low porosity substrates, use a solvent-free epoxy primer R 3 E, or water based epoxy primer WPM 300 and blind with sand (~ 0.5 – 1mm). Allow the primer to cure to a hard film (24 hours) before proceeding. Once cured, sweep the surface with a stiff bristle push broom and then thoroughly vacuum to remove all loose sand before application of leveler.

Do NOT install leveling compounds until the primer has thoroughly dried or cured. Refer to the relevant product datasheet for specific instructions in relation to each primer.

MIXING

5 L of clean water per 25 kg bag of K 180. The water mixing ratio might be affected by environment & site conditions as well as mixing devices. Please always conduct a flow ability test to determine whether the water mixing ratio should be slightly adjusted before application of large areas.

ARDEX ENDURA floor leveling products react and harden quickly when mixed with water. Thorough mixing with a heavy duty electric drill fitted with an ARDEX ENDURA mixing paddle in the shortest possible time is essential.

Always mix the powder into the water.

The normal mixing time for a 25 kg bag is 1½ - 2 minutes.

Concrete or screed mixers, paint mixers, spiral mixers and hand mixing are not suitable.

INSTALLATION

K 180 can be applied in temperature ranges (substrate & atmospheric) from 10° - 35°C.

K 180 has a flow time of approx. 20 minutes at 23°C. At lower temperatures this time is extended and at higher temperatures this time is shortened.

Work to an area that suits the size of the installation team such that fresh mortar is poured into workable mortar, which can then be spread, gauged and troweled within the flow time of the material.

Pour the mixed K 180 material onto the prepared & primed substrate and then spread into place using appropriate tools.

K 180

High Strength Self-leveling Compound

Rake the material to gauge the thickness as necessary and then smooth the surface with a flat trowel if required. The use of a spiked roller may aid the final leveling of the material, but is not normally necessary. If used, the spiked roller should be used within the flow time of the product and limited to a maximum of 4 passes.

Studded shoes should be worn when walking in the fresh mortar to avoid leaving marks.

For ease & efficiency in applying material in large areas, K 180 can be pumped with continuously working auger or piston style pumps with a capacity of 20 – 40L of mortar per minute. If the pumps are not in operation for 15 minutes they should be cleaned.

Protect the surface of the setting material from wind, sunlight and contamination for 24 hours.

The application of a small test area prior to complete installation is recommended in unusual circumstances.

APPLICATION THICKNESS

K 180 can be applied from 4 – 10mm in one application.

Gradient smoothing and ramping may be achieved by water reduction and the addition of fine, clean & dry sand.

For further information,

For further information, contact ARDEX ENDURA Technical Services.

CURING & DRYING TIMES

Walkability

Allow approximately 4 hours at 23°C before foot traffic.

Application of Industrial Floor Coatings

The hardened K 180 should be protected from wear (abrasion) and staining (water, oil, salt, chemicals) by applying a suitable stain & wear protection system. This can be in the form of an epoxy or polyurethane coating.

In general, water-based coatings can be applied after 24 hours whilst solvent-free or moisture-sensitive systems can be applied 48-72 hours after curing.

Refer to the relevant product datasheet or Manufacturers' instructions for specific application and usage details in relation to the chosen floor covering.

Full Cure

K 180 will gain sufficient strength after 16 hours to allow access for the commencement of finishing or light-medium traffic activity.

Allow 7 days curing at 23°C before subjecting the material to full service conditions.

Note:- higher temperatures may reduce curing & drying times, whilst lower temperatures will extend the drying time.

CLEAN-UP

Clean all tools, equipment, hands, etc with water immediately after use. Hardened material will have to be removed using mechanical means.

COVERAGE ESTIMATES

Pack size

25 kg

Coverage

approx. 1.75kg/m²/mm

Thus a 25kg bag will cover approximately 2.85m at 5mm thickness – assuming a flat surface.

STORAGE AND SHELF LIFE

K 180 has a shelf life of approximately 6 months if stored in dry conditions in the original un-opened packaging

TECHNICAL DATA

General

In Accordance with ARDEX ENDURA Quality Standards

Powder

Mixing Ratio: 5 L Water to 25kg Powder

Bulk Density of Powder: ~1.4kg/L

Consumption: ~1.75kg powder/mm/m

Wet- Fresh-Mixed Mortar

Application Temperature: 10°C – 35°C Mixed

Mortar Density: ~ 2.1kg/L

pH of Fresh Mortar: ~ 12

Flow Time (23 C): ~ 20 minutes

Walkability (23 C): ~ 4 hours

Application Thickness: 4 – 10mm Thickness

with Aggregate 10 – 25mm

Cured Mortar

Ready for Floor Coating (23°C / 50%RH):

~ 1-3 days

Resistant to Chair Castors: Yes

Suitable with Floor Heating: Yes

Moisture Tolerant: Intermittent: Yes;

Flooding: No

Freeze-Thaw Stable: No

In Accordance with Chinese National Standard:- JC/T985-2017

Flow

Initial: > 135mm

After 20 minutes: > 130mm

Compressive Strength

After 1 day: ~ 12 Mpa

After 28 days: ~ 40 Mpa

Flexural Strength

After 1 day: ~ 4 Mpa

After 28 days: ~ 8.5 MPa

Adhesion Strength: ~ 1.8 Mpa

Shrinkage: - 0.1%

Impact Resistance: No cracks or de-lamination

HEALTH & SAFETY

K 180 is considered nonhazardous in normal usage, however it contains Portland cement & quartz sand and reacts alkaline which may cause some skin irritation after prolonged contact. Avoid generation and breathing of dust. Avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety

K 180

High Strength Self-leveling Compound

glasses. In case of contact with eyes, rinse for several minutes under running water. In case of contact with skin, rinse with running water. If dust is inhaled, remove to fresh air, ensure breathing passages are clear and rinse mouth with water. In the case of adverse symptoms, seek medical advice.

Physiologically and ecologically safe when in the cured state.

For more details please refer the relevant Material Safety Data Sheet

CONDITIONS OF SALE

Sold subject to the Company's conditions of sale which are available on request.

NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.



ARDEX ENDURA (INDIA) PRIVATE LIMITED

an ISO 9001:2015 & ISO 14001:2015 certified company
Corporate Office & Regd. Office: Unit No. 406 & 407,
"Brigade Rubix" No. 20, HMT Campus,
Yeshwanthpur Hobli, Bengaluru - 560013.
CIN No: U24233KA1997PTC022383 Tel: +91 80 66746500
Email: customer-care@ardexendura.com
Website: www.ardexendura.com

Branches

• AHMEDABAD	079 26425310	• HUBBALLI	0836 2970505	• NAGPUR	+919822223743
• AURANGABAD	+918605445577	• HYDERABAD	040 27650293	• PATNA	+919934687909
• BENGALURU:	080 40912934	• INDORE	0731 4021148	• PUNE	020 64781879
• BHUBANESHWAR	0674 2578101	• JAIPUR	0141 2392993	• RAIPUR	0771 4038300
• CALICUT	0495 2460334	• KOLKATA	+919831071084	• SALEM	0427 2211454
• CHENNAI	044 42805544	• LUCKNOW	0522 4043251	• SHIVAMOGGA	+919880605770
• DELHI	+919810603431	• LUDHIANA	0161 2532170	• TRICHY	0431 6454649
• ERNAKULAM	0484 2341044	• MANGALURU	0824 2442176	• TRIVANDRUM	0471 2598648
• GOA	0832 2750992	• MUMBAI	022 65133299	• VIJAYAWADA	+918688354587
• GUWAHATI	+917896002188	• MYSURU	0821 2570171	• VISAKAPATNAM	0891 6469499